

SAKRETE®

SAND MIX

DESCRIPTION

A ready to use mixture of sand and portland cement. Ingredients are mixed to meet specified strength requirements.

USES

To be used where a thickness of less than 5.08 cm (2") is required. For filling cracks in concrete and between flagstone, grouting, parging, etc. Can be finished smooth.

DIRECTIONS

Empty contents of sack into mortar box, wheel barrow or onto a smooth surface. Form a crater for adding water. Add clean water at the rate of 4 litres (3 ½ quarts) per 30 kg bag and mix thoroughly. If sand mix is too stiff, add more water, a cupful at a time. Avoid a soupy mix. In cold weather use warm water to accelerate the set. Protect from freezing until cured. In repairing concrete, square up opening to be patched. Remove loose materials and clean surfaces thoroughly. Dampen surface just before applying SAKRETE Sand Mix. When filling cracks, tamp SAKRETE Sand Mix with a rod or stick. Level with a straight edged board. After leveling, allow fresh SAKRETE Sand Mix to set about one (1) hour before troweling. Allow to set for one (1) day, then keep moist for at least three (3) days by an occasional fine spraying of water.

PACKAGING

Packaged in 30 kg (66 lb) multi-ply, moisture proof bags.

BAG COVERAGE

30 kg (66 lb) approximately 1.2 m² at 1.27 cm thickness (13 sq. ft. at ½ inch).

Wet volume: .014 m³ (½ cu. ft.)

SPECIFICATIONS

Will meet or exceed 4,000 PSI (27 MPA). Exceeds strength requirements of A.S.T.M. Spec. C-387 when used as directed.

IMPORTANT

Store in a dry place.

CAUTION

Avoid contact with eyes. Avoid ingestion or inhalation. Contains cement which when mixed with water, forms a calcium hydroxide solution. Avoid contact with skin, including contact with saturated clothing.

FIRST AID TREATMENT: If splashed in eyes or on skin, flush thoroughly with water.